

# INLAND PLASTICS Ltd.



MANUFACTURER AND DISTRIBUTOR

2005

## POLYFABRIC SPECIFICATION SHEET Q1212-8.5

( ) HEAD OFFICE  
P.O. Box 2199  
Drumheller, AB  
T0J 0Y0  
Ph: (403) 823-6252  
Fax: (403) 823-7310

( ) BRANCH  
1645 Enterprise Road  
Mississauga, ON  
L4W 4L4  
Ph: (905) 670-3000  
Fax: (905) 670-3003

( ) BRANCH  
842 - 56 St. E.  
Saskatoon, SK  
S7K 5Y8  
Ph: (306) 931-1122  
Fax: (306) 934-7078

( ) BRANCH  
Unit 206, 9775 - 188 St.  
Surrey, BC  
V4N 3N2  
Ph: (604) 882-1469  
Fax: (604) 882-1460

( ) BRANCH  
1590 Grinell Road  
Kankakee, IL 60901  
Ph: (815) 933-3500  
Fax: (815) 933-4500

( ) BRANCH  
6100 - 58 Ave., Unit D  
Commerce City, CO 80022  
Ph: (303) 853-8886  
Fax: (303) 853-4744

General Description: High density polyethylene woven fabric base complete with a low density coating.

		<u>Test Method</u>
Denier of Tapes:	1600D (Natural)	
Construction (tapes/inch):	warp 12 / weft 12	
Coating:	3 mil / both sides	
Weight:	8.5oz p.s.y.	
Tensile Grab Strength:	240/240	ASTM D5034
Grab Tear:	warp 75 / weft 77	ASTM D2261
Burst:	460 PSI	ASTM D3786
Puncture:	140lbs	ASTM D4833
Thickness:	16 mil	
Standard Width:	144"	
Standard Colours:	Black / Black	

We believe this information is the best currently available on the subject. We make no guarantee of results and assume no obligation or liability in connection with this information. It is offered as a possible helpful suggestion in any experimentation you may care to undertake along these lines.